TOA SHARK WOOD STAIN GLOSS

Technical Data Sheet

Rev.1 10/2017

FEATURES

Shark Wood Stain Gloss is based on flexible alkyd resin, special additives and transparent pigments. The properties of this product are high gloss, high film build, waterproof, good leveling, anti-fungi, and good UV resistance.

Suitable for exterior and interior protection of all woodworks such as wooden house, wooden boat, wooden furniture and etc.

TECHNICAL INFORMATION

Type	Alkyd Resin	
Color	Wide range of colors. Please ask for catalog.	
Film appearance	Gloss	
Solid by volume	NA	
Solid by weight	50.0 ± 5.0	%
Flash point	40.0	˚C
Volatile organic compounds (VOCs)	NA	
Wet film thickness	100	microns
Dry film thickness	45	microns
Theoretical coverage.	45 – 55	sq.m. / gallon / coat
	Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.	
Touch dry (25-30˚C)	2-3	hours.
Recoat dry (25-30˚C)	8-10	hours.
Full cure (25-30˚C)	7	days.

REFERENCE STANDARD

-

APPLICATION

Tools	Brush, Spray	
Thinner No.	TOA Enamel Thinner No.21 (or Drying Oil or Turpentine Oil)	
Dilution (%)	5-10	% (roller and brush)
	20-25	% (spray)

APPLICATION SYSTEM

Surface Preparation

Old surface

For coated wood or wood with old or peeling paint film or old wood with no coating.
Sand with abrasive paper to the wood surface.For coated wood which coating film still in good condition.
Sand over the painted film with TOA Abrasive Paper No.240-320
then clean the surface to remove grease, dust, oil or dirt.

New surface

1. Use TOA abrasive paper no. 240 – 320 to sand the wood surface until smooth.
2. Fill all wood crack and hole by filler.
3. Sand again until the smooth surface is obtained.
4. Clean the surface until no dust remain.

TOA SHARK WOOD STAIN GLOSS

Technical Data Sheet

Rev.1 10/2017

Coating system

Primer

Apply by brush with TOA Wood Preservative 1 coat. (Recoatable time is at least 30 minutes)

Topcoat

1. Mixing ratios between Shark Wood Stain Gloss and TOA Thinner No.21 are 5:1 for first coat and 10:1 for second and third coat, respectively.
2. Apply by brush with **Shark Wood Stain Gloss** at least 3 coats. (Recoatable time is at least 8 hours)
3. Before topcoat any layer, TOA abrasive paper no. 320 – 400 are recommended to sand the surface which provide good intercoat adhesion and smooth the surface.

Recommendation

: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure correct drying.

HANDLING AND STORAGE

Storage condition

: The product must be stored in accordance with national regulations.
Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.
Containers must be kept tightly closed.

Shelf life

: 2 years.

HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with s uitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

ทีโอเอ วู้ดสเตน ตราปลาฉลาม ชนิดเงา

ข้อมูลทางวิชาการ

ทบทวน ครั้งที่ 1 10/2560

คุณสมบัติ

วู้ดสเตน ตราปลาฉลาม ชนิดเงา ผลิตจาก แอลคีดเรซิน ที่มีความยืดหยุ่น มีส่วนผสมของสารเติมแต่งชนิดพิเศษ และแม่สีชนิดโปร่งแสง ให้ฟิล์มสีที่เรียบ มีความเงาสูง ทาแล้วขึ้นฟิล์มเร็ว ป้องกันน้ำซึมได้ดี มีส่วนผสมของสารป้องกันเชื้อราและสามารถทนต่อสภาวะอากาศภายนอกและแสงยูวีได้ดี
เหมาะสำหรับงานโครงสร้างไม้ภายนอกและภายใน เช่น บ้านไม้ และ เรือไม้แบบต่างๆ รวมถึง เฟอร์นิเจอร์ที่ทำจากไม้

ข้อมูลทางเทคนิค

ประเภทสี	แอลคีดเรซิน	
เฉดสี	เลือกเฉดสีได้จากแคตตาล็อก	
ลักษณะฟิล์มสี	ชนิดเงา	
เนื้อสีโดยปริมาตร	ไม่มีข้อมูล	
เนื้อสีโดยน้ำหนัก	50.0 ± 5.0	%
จุดวาบไฟ	40	˚C
ปริมาณสารอินทรีย์ระเหยได้	ไม่มีข้อมูล	
ความหนาฟิล์มสีเมื่อเปียก	100	ไมครอน
ความหนาฟิล์มสีเมื่อแห้ง	45	ไมครอน
การครอบคลุมพื้นที่ตามทฤษฎี	45 – 55	ตารางเมตร ต่อ แกลลอน ต่อ เที่ยว
	หมายเหตุ : การผสม, การใช้งาน, ความหยาบและรูพรุนของพื้นผิว มีผลต่อค่าการปกคลุมพื้นผิว	
ระยะเวลาแห้งสัมผัส (อุณหภูมิ25-30˚C)	2-3	ชั่วโมง
ระยะเวลาแห้งทาทับ (อุณหภูมิ25-30˚C)	8-10	ชั่วโมง
ระยะเวลาแห้งสมบูรณ์ (อุณหภูมิ25-30˚C)	7	วัน

มาตรฐานอ้างอิง

-

วิธีใช้งาน

อุปกรณ์	แปรงขนอ่อน หรือ ปืนพ่น	
ทินเนอร์	ทีโอเอ ทินเนอร์ #21 (หรือน้ำมันสน หรือน้ำมันซักแห้ง)	
การผสมทินเนอร์ (%)	5-10	% (กลิ้ง หรือ ทา)
	20-25	% (พ่น)

ระบบการใช้งาน

การเตรียมพื้นผิว

พื้นผิวเก่า

กรณีไม้เคยทาสีมาก่อนและฟิล์มสีลอกล่อน หรือ เป็นไม้เก่าที่ไม่เคยทำสีมาก่อน ให้ขัดด้วยกระดาษทรายจนถึงเนื้อไม้เดิม
กรณีที่ฟิล์มสียังมีพื้นไม้อยู่ในสภาพดี ให้ลูบผิวฟิล์มด้วยกระดาษทรายขัดแห้ง ทีโอเอ เบอร์ 240 – 320
แล้วทำความสะอาดพื้นผิวให้ปราศจากคราบไขมัน ฝุ่น น้ำมัน หรือสิ่งแปลกปลอม

พื้นผิวใหม่

1. ใช้กระดาษทรายขัดแห้ง ทีโอเอ เบอร์ 240 – 320 ขัดแต่งพื้นผิวจนเรียบสวย
2. อุดโป๊วรอยแตก ตำหนิบนไม้และหัวตะปู ให้เรียบร้อย
3. ขัดแต่งด้วยกระดาษทรายอีกครั้ง จนได้พื้นผิวที่เรียบเนียน
4. เช็ดทำความสะอาดพื้นผิว

ทีโอเอ วู้ดสเตน ตราปลาฉลาม ชนิดเงา

ข้อมูลทางวิชาการ

ทบทวน ครั้งที่ 1 10/2560

ระบบการทาสี

สีรองพื้น	ทารองพื้นด้วย ทีโอเอ น้ำยารักษาเนื้อไม้ จำนวน 1 เที่ยว (ทิ้งให้แห้งอย่างน้อย 30 นาที ก่อนทาทับเที่ยวต่อไป)
สีทับหน้า	1. การผสม วู้ดสเตน ตราปลาฉลาม ชนิดเงา กับ ทีโอเอ ทินเนอร์ เบอร์ 21 การทาเที่ยวที่ 1 แนะนำให้ผสมสี 5 ส่วน ต่อ ทินเนอร์ 1 ส่วน การทาเที่ยวที่ 2 และ 3 แนะนำให้ผสมสี 10 ส่วน ต่อ ทินเนอร์ 1 ส่วน 2. ทาด้วย วู้ดสเตน ตราปลาฉลาม ชนิดเงา อย่างน้อย 3 เที่ยว (ทิ้งให้แห้งอย่างน้อย 8 ชั่วโมง ก่อนทาทับเที่ยวต่อไป) 3. ก่อนทาหรือพ่นทับหน้าเที่ยวต่อไป ให้ขัดแต่งพื้นผิวด้วยกระดาษทรายขัดแห้ง ทีโอเอ เบอร์ 320 – 400 เพื่อเพิ่มการยึดเกาะและได้พื้นผิวชิ้นงานที่เรียบ
ข้อแนะนำการปฏิบัติงาน	: อุณหภูมิของชิ้นงานจะต้องสูงกว่า 10˚C และสูงกว่าจุดน้ำค้างอย่างน้อย 3˚C อุณหภูมิและความชื้นสัมพัทธ์ต่างมีผลต่อชิ้นงานและการแห้งตัวของฟิล์มสี

การเก็บรักษา

สภาวะการเก็บรักษา	: จัดเก็บสินค้าในที่แห้ง มีอากาศถ่ายเทดี ปิดฝาให้สนิท ให้แน่นตลอดเวลา ไม่ควรเก็บในที่ร้อนและไม่ให้ถูกแสงแดดโดยตรง
อายุผลิตภัณฑ์	: 2 ปี

ข้อมูลสุขภาพและความปลอดภัย

: กรุณาดูข้อควรระวังที่ติดไว้บนภาชนะบรรจุ การทำงานสีควรทำในที่ที่อากาศถ่ายเทสะดวก
ควรใส่หน้ากากเมื่อทำการพ่นสีและพยายามเลี่ยงมิให้สัมผัสผิวหนัง หรือสูดดม
ถ้าสีหกใส่ผิวหนังควรล้างด้วยน้ำสะอาดกับสบู่ทันที ถ้าสีเข้าตาควรล้างด้วยน้ำสะอาดทันทีและรีบไปพบแพทย์
: รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในข้อมูลด้านความปลอดภัย

การสงวนสิทธิ์เรียกร้อง

: รายละเอียดข้างบนนี้ได้มาโดยการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไปใช้ในสภาวะแตกต่างกันเราจึงไม่สามารถรับประกันในสิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น
บริษัทขอสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมิต้องแจ้งล่วงหน้า