INSEE MORTAR 12

INSEE MORTAR 12: Fine Plastering Mortar

is a dry-mixed mortar consisting of Portland cement , special quality grade limestone sand and additives for providing high water retention , excellent workability, fine-smooth surface, and high adhesion strength capabilities. The finished surfaces are smooth and free of cracks.



Applications

IM Fine Plastering Mortar 12 is formulated for is formulated for plastering on clay brick and concrete block walls, both interior and exterior, which require special fine-smooth surface.

Recommendations

- Cure the finished surface with water for 2-3 days.
- Wet mortar should be used within 2 hours.

Storage

- Keep the dry mortar bags in dry and no humidity storage.
- Do not store the dry mortar bags longer than 2 months.

Work Instructions

IM Fine Plastering Mortar 12 provides advantages such that it helps to reduce complicated material preparation, facilitates conventional working procedures, and enables to obtain higher performance of work. General application includes:

1. Clean the substrate to be free from dust, oil, curing compound, grease or any surface contaminants.
2. Moisten the substrate appropriately before plastering.
3. Mix uniformly IM Fine Plastering Mortar 12 with recommended amount of clean water.
4. Apply the mortar firmly onto the substrate according to conventional plastering technique. Allow 1 - 1.5 cm thickness.

Typical Data and Property

Availability	:	50 kg bags
Mix Proportion	:	11 - 14 liters of water per bag
Application Area	:	2.5 - 2.8 sq m at 1 cm thickness
Compressive strength	:	> 2.5 MPa at 28 days