Fine Plaster Mortar TPI M100



Recommend : - After mixing with water, it should be applied within 2 hours 30 minutes (1 bag (50 kg.) per 12 liters of water) Keep in a dry place away from moisture and seal tightly.

Product Characteristic

Ready - mixed plaster mortar is suitable for plastering wall surface which gives special fine and smooth surface. Suitable to use with brick or concrete block both indoor and outdoor, it conforms to TIS 1776 - 2542 Thai Industrial standard.

Raw Materials

- TPI Portland Cement Type 1 conforms to ASTM C- 150 and TIS 15 - 2555
- Fine limestone which is throughly dried and classified.
- High quality chemical additives improving workability and reduce cracking.

How to use

1. Clean and rinse water on the wall surface.
2. Mix TPI (M100) with clean water at ratio 3:1 by volume
3. Mix well until the mixture is homogeneous.
4. Ready to apply with a common plastering procedure, it can also be applied with mortar plastering Machine.

Area Recommended

Thickness of plastering (MM)	Plastering Area per 1 bag (50 kg.) (sq.m)	Quantity per square (kg.)
10	2.88	17
15	2.16	23





Suitable for fine plastering work with brick and concrete block