Plaster Mortar M200

Product Characteristic

A ready mixed plastering mortar suitable for a general plastering works on and concrete block for both indoor walls application.
it conforms to TIS 1776 - 2542. Thai industrial standard.

Raw Material

- TPI portland Type 1 according to standard ASTM C - 150 and TIS 15 part 1-2547
- Fine Limestone is throughly dried and classified.
- High quality chemicals additives that improve water absorption, better work ability and reduces cracking and prevents shrinking.

Remark:

- If the thickness of plaster is more than 1 cm, it shoud be applied layer by layer. Leave it till it sets to dry before starting with the next layer.
- 1 bag (50 kg.) mix with 11 liter of wark.

How to use

1. Clean and rinse through the surface on the wall to be plasteried.
2. Mix Plaster Mortar TPI (M200) with clean water 3.5 ratio.
3. Mix it with water until the mixture is homogeneous.
4. Ready to process with the ordinary works and it can also be used with plastering machines.

Area Recommended

Thickness / (MM)	1 bag (50 KG.) Plastering Area (sq.m)	Quantity per sq.meter
10	2.88	17
15	2.16	23

Suitable for common plaster work with brick and concrete block.