Lightweight Block Plaster Mortar

M210

Product Characteristic

A special ready - mixxed mortar is formulated for plastering work on light weight blocks for both indoor and outdoor walls application. Also able to apply on red brick wall and concrete block wall as well.

Raw Material

- TPI Portland Type 1 according to standard ASTM C -150 and 15 part 1- 2555.
- Fine Limestone is throughly dried and classified
- High quality chemical additives providing water absorption improving, workability , adhesion and prevents shrinkage.

How to use

- Clean and rinse the surface area on the wall which will be plasteried
- Mix Plaster Mortar TPI (M200) with clean water 3:1 partial.
- Mix it with water until the mixture is homogeneous.
- Ready to process with the ordinary plastering works, but can also be applied with plastering machines.

Remark:

- After mixing with water, it should be applied within 2 hours 30 minutes (1 bag (50 kg.) per 11 liters of water). Keep in a dry place away from moisture and seal tightly

Area Recommended

Thickness/(MM.)	1bag(50KG.) Plastering Area (sq.m)	Quantity per sq. meter (kg)
10	2.88	17
15	2.16	23

Suitable for Lightweight block plastering especially