

Mortar for Production Lightweight Block

M220B



Product Characteristics

Ready - mixed mortar for production of Lightweight block (Cellular Lightweight Concrete: CLC) by mixing with foaming agent and water according to the ratio precribed.

How to prepare

- Mix TPI M220B 1 bag (50kg) with 7.0 Liters of water and mix well
- Add foaming agent according to the ratio of the manufacturer and mix until mixture it homogeneous. After that pour the mixture into the mold.
- Let the mortar set for about 2 hours, then remove the block out of mold before cutting to the required size.



Usage Quantities (For production Lightweight block size 20x60x7.5 cm)

Number of bags (bag)	Amount of mortar (kg)	Number of Lightweight block production (Pieces)
20	1.000	120

Suitable for production Lightweight block (Cellular Lightweight Concrete : CLC)