TOA SUPERTECH LACQUER PRIMER SURFACER # 1570

Technical Data Sheet

Rev.1. 10/2017

FEATURES

Supertech Lacquer Primer Surfacer # 1570 is based on Nitrocellulose, Alkyd Resin and high quality pigments. Properties of the products are fast dry, easy to sand, good hiding power, excellent adhesion on plywood, MDF and solid wood.

Recommend to use as primer for ply wood, MDF, solid wood and interior wood furniture.

TECHNICAL INFORMATION

Type	Nitrocellulose Solution and Alkyd Resin	
Color	White	
Film appearance	Matt	
Solid by volume	NA	
Solid by weight	47.0 ± 2.0	%
Flash point	21	˚C
Wet film thickness	100	microns
Dry film thickness	45	microns
Theoretical coverage.	45 - 50	sq.m. / gallon / coat
	Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.	
Touch dry (25-30˚C)	5 - 10	minutes.
Recoat dry (25-30˚C)	20	minutes. (minimum)
Full cure (25-30˚C)	1 - 2	hours

REFERENCE STANDARD

-

APPLICATION

Tools	Brush, Spray
Thinner No.	TOA Lacquer Thinner # 71
Dilution (%)	100 - 150 % (brush)
	150 - 200 % (spray)

APPLICATION SYSTEM

Surface Preparation

Old surface

1. Chalky surfaces or loose material must be removed by stiff brush.
2. The surfaces must be clean and free of dirt,wax,salt,old paint and other contaminants.

New surface

1. Use TOA abrasive paper no. 240 - 320 to sand the wood surface until smooth.
2. Fill all wood crack and hole by filler.
3. Sand again until the smooth surface is obtained.
4. The surfaces must be clean and free of dirt, grease, oil, wax, salt and other contaminants.

Coating system

Primer

Apply by brush or spray with Supertech Lacquer Primer Surfacer # 1570 at least 2 coats. (Recoatable time is at least 20 minutes)

Topcoat

Apply by brush or spray with Supertech Industrial Lacquer at least 2 coats.

Before topcoat any layer, TOA abrasive paper no. 320 – 400 are recommended to sand the surface

Technical Data Sheet

Rev.1. 10/2017

Recommendation : The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure correct drying.

HANDLING AND STORAGE

Storage condition : The product must be stored in accordance with national regulations.
Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.
Containers must be kept tightly closed.

Shelf life : 2 years (from manufacturing date)

HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with s uitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

ทีโอเอ สีพ่นรองพื้นชนิดแห้งเร็ว ซุปเปอร์เทค # 1570

ข้อมูลทางวิชาการ

ทบทวน ครั้งที่ 1 10/2560

คุณสมบัติ

สีพ่นรองพื้นชนิดแห้งเร็ว ซุปเปอร์เทค # 1570 ผลิตจากอัลคีด เรซิน, ไนโตรเซลลลูโรส ผงสีคุณภาพสูง ให้ฟิล์มสีที่แห้งไว ขัดง่าย กลบปิดพื้นผิวได้ดี สามารถยึดเกาะบนผิว ไม้อัด ไม้ MDF และไม้จริงได้ดีเยี่ยม เหมาะสำหรับงานรองพื้นไม้อัด, ไม้ MDF, ไม้จริง และ เฟอร์นิเจอร์ไม้ภายใน

ข้อมูลทางเทคนิค

ประเภทสี	ไนโตรเซลลูโรสโซลูชั่น และ อัลคีด เรซิน	
เฉดสี	ขาว	
ลักษณะฟิล์มสี	ด้าน	
เนื้อสีโดยปริมาตร	ไม่มีข้อมูล	
เนื้อสีโดยน้ำหนัก	47.0 ± 2.0	%
จุดวาบไฟ	21	˚C
ความหนาฟิล์มสีเมื่อเปียก	100	ไมครอน
ความหนาฟิล์มสีเมื่อแห้ง	45	ไมครอน
การครอบคลุมพื้นที่ตามทฤษฎี	45 - 50	ตารางเมตร ต่อ แกลลอน ต่อ เที่ยว
	หมายเหตุ : การผสม, การใช้งาน, ความหยาบและรูพรุนของพื้นผิว มีผลต่อค่าการปกคลุมพื้นผิว	
ระยะเวลาแห้งสัมผัส (อุณหภูมิ25-30˚C)	5 - 10	นาที
ระยะเวลาแห้งทาทับ (อุณหภูมิ25-30˚C)	20	นาที (เป็นอย่างน้อย)
ระยะเวลาแห้งสมบูรณ์ (อุณหภูมิ25-30˚C)	1 - 2	ชั่วโมง

มาตรฐานอ้างอิง

-

วิธีใช้งาน

อุปกรณ์	แปรงทาสี เครื่องพ่น
ทินเนอร์	ทีโอเอ แล็กเกอร์ ทินเนอร์ เบอร์ 71
การผสมทินเนอร์ (%)	100 - 150 % (ทา)
	150 - 200 % (พ่น)

ระบบการใช้งาน

การเตรียมพื้นผิว

พื้นผิวเก่า

1. ควรขัดสีเก่าที่เสื่อมสภาพหรือวัสดุต่างๆบนพื้นผิวเดิมออกก่อน
2. เช็ดทำความสะอาด พื้นผิวต้องปราศจากสิ่งสกปรก, คราบน้ำมัน, คราบเกลือ, สีเก่าและสารปนเปื้อนอื่นๆ

พื้นผิวใหม่

1. ใช้กระดาษทรายขัดแห้ง ทีโอเอ ดีเอสซี #240 – 320 ขัดแต่งพื้นผิวจนเรียบสวย
2. อุดโป๊วรอยแตก ตำหนิบนไม้และหัวตะปู ให้เรียบร้อย
3. ขัดแต่งด้วยกระดาษทรายอีกครั้ง จนได้พื้นผิวที่เรียบเนียน
4. เช็ดทำความสะอาด พื้นผิวต้องปราศจากสิ่งสกปรก, คราบน้ำมัน, คราบเกลือและสารปนเปื้อนอื่นๆ

ระบบการทาสี

สีรองพื้น

ทาหรือพ่นรองพื้นด้วย สีพ่นรองพื้นชนิดแห้งเร็ว ซุปเปอร์เทค # 1570 อย่างน้อย 2 เที่ยว
(ทิ้งให้แห้งอย่างน้อย 20 นาทีก่อนทา หรือ พ่นทับเที่ยวต่อไป)

สีทับหน้า

ทาหรือพ่นด้วย สีพ่นอุตสาหกรรม ซุเปอร์เทค อย่างน้อย 2 เที่ยว
ก่อนทาหรือพ่นทับหน้าเที่ยวต่อไป ให้ขัดแต่งพื้นผิวด้วยกระดาษทราย ทีโอเอ ดีเอสซี #320 – 400
เพื่อเพิ่มการยึดเกาะและได้พื้นผิวชิ้นงานที่เรียบ

ข้อแนะนำการปฏิบัติงาน

: อุณหภูมิของชิ้นงานจะต้องสูงกว่า 10˚C และสูงกว่าจุดน้ำค้างอย่างน้อย 3˚C
อุณหภูมิและความชื้นสัมพัทธ์ต่างมีผลต่อชิ้นงานและการแห้งตัวของฟิล์มสี

ข้อมูลทางวิชาการ

ทบทวน ครั้งที่ 1 10/2560

การเก็บรักษา

สภาวะการเก็บรักษา : จัดเก็บสินค้าในที่แห้ง มีอากาศถ่ายเทดี ปิดฝาให้สนิท ให้แน่นตลอดเวลา ไม่ควรเก็บในที่ร้อนและไม่ให้ถูกแสงแดดโดยตรง

อายุผลิตภัณฑ์ : 2 ปี (นับจากวันที่ผลิต)

ข้อมูลสุขภาพและความปลอดภัย

: กรุณาดูข้อควรระวังที่ติดไว้บนภาชนะบรรจุ การทำงานสีควรทำในที่ที่อากาศถ่ายเทสะดวก ควรใส่หน้ากากเมื่อทำการพ่นสีและพยายามเลี่ยงมิให้สัมผัสผิวหนัง หรือสูดดม ถ้าสีหกใส่ผิวหนังควรล้างด้วยน้ำสะอาดกับสบู่ทันที ถ้าสีเข้าตาควรล้างด้วยน้ำสะอาดทันทีและรีบไปพบแพทย์

: รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในข้อมูลด้านความปลอดภัย

การสงวนสิทธิ์เรียกร้อง

: รายละเอียดข้างบนนี้ได้มาโดยการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไปใช้ในสภาวะแตกต่างกันเราจึงไม่สามารถรับประกันในสิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น

บริษัทขอสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมิต้องแจ้งล่วงหน้า