
LANKO 103 SKIMCOAT PLUS

Rendering

INTERIOR AND EXTERIOR WALL AND CEILING SKIMCOAT





Interior | Can Spray | Trowel | Can Paint Over

CHARACTERISTICS

- **Thickness: 0.3 to 5 mm.**
- **Smooth finish.**
- **Can be exposed or covered.**
- **UV resistance.**
- **Time saving.**
- **White.**

DESCRIPTION

A ready-to-use skim paste for levelling uneven surface and filling small bubbles.

USES

- Interior/Exterior.
- Wall/Ceiling.
- Substrates: concrete, render, brick and gypsum, light weight concrete.

WORK INSTRUCTIONS

Surface Preparation

1. Surface must be clean, dry, and free of dust, oil, paint.
2. Damage concrete, seams and rock pockets exceeding 3 mm. must be treated prior to application.

Product Preparation

1. Ready-to-use paste. No. water must be added.

Application

1. Apply 1st coat with stainless trowel or spray.
2. A minimum of 2 coats are required to obtain a satisfactory surface.
3. Allow sufficient drying time so that is not drawn off while applying 2nd coat.
4. Use sand paper to obtain a smooth finish.
5. Allow 24 hours curing time before applying covering material.

COVERAGE

- 0.5-1.5 kg./sq.m./mm.

PACKAGING

- 5 kg. bucket.
- 20 kg. bucket.

STORAGE

- 1 year from date of manufacture if stored in unopened original packaging in dry condition.

PAREX GROUP
Building expertise, together

Note : As a primer for light weight block, at a rate of 1 part of LANKO 751 LATEX for 2 parts of clean water.

PRECAUTIONS

- Temperature range for use : 5°c to 35°c.
- Do not apply to damp substrate.
- Protect for 24 hours in case of heavy rain or hard sun.
- Do not add any water or other product.
- Do not cover with a hydraulic binder mortar.

SPECIFICATIONS

Appearance	:	**White Paste**
Main composition	:	**Synthetic Resins**
Drying time before 2nd coat (Hours)	:	**3-4 Hours**
Time before covering (Days) Paste	:	**3 Days**
Paste density (kg./L.)	:	**1.7-1.8 kg./L.**
pH	:	**8-10**

Bonding strength on concrete (MPa)	Evaluation
28 days : 1 mm. thickness	> 0.5
28 days : 3 mm. thickness	> 0.5

094 551 5458 02 651 8003 parexgroup.co.th e-learning VDO

ParexGroup Company Limited. 183 Regent House Building, Rajdamri Road., Lumpini, Bangkok 10330

*The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the lasted version of this document.