TOA SUPERSHIELD ALKALI RESISTING PRIMER

Technical Data Sheet

Rev.1 10/2017

FEATURES

It is an ideal primer for the new masonry surface where the alkalinity is likely the cause paint defect for the subsequent coating system.Beacuse it is base on high quality latex, it effectively resists saponification on lime plaster, asbestos cement or concrete.It contains a mold control additive Typical Use;It is ideal application to both exterior and interior concretes, new and old masonry surface, plasters, brick, asbestos shingles and siding.It is highly recommended for heat protection of building and housing.

TECHNICAL INFORMATION

Type	100% Acrylic Emulsion	
Color	White	
Film appearance	Matt	
Solid by volume	32-34	%
Solid by weight	52-54	%
Flash point	N/A	˚C
Volatile organic compounds (VOCs)	less than 10	gram / litre
Wet film thickness	100-110	microns
Dry film thickness	35-40	microns
Theoretical coverage.	35-45	sq.meter / gallon / coat
	Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.	
Touch dry (25-30˚C)	30	minutes
Recoat dry (25-30˚C)	2	hours
Full cure (25-30˚C)	7	days

REFERENCE STANDARD

TIS 1123-2555(2012)(Masonry Primer),
Green Label Thailand

APPLICATION

Tools	Roller, Brush, Spray	
Diluent	Clean Water	
Dilution (%)	10-20	% (roller and brush)
	20-25	% (spray)
	The dilution could be done depends on the variation of temperature and humidit atmosphere.The given figure is the average data from actual use.	

APPLICATION SYSTEM

Surface Preparation

New surface

Substrate must be completely cured and dried (~1 month) free from oil, grease, mildew.
Areas where the fungus to kill mold polished clean with liquid TOA Microkill.Cleaning. Then let it dry 1-2 days.
At a crack width less than 1 mm. and not break continuity.
Putty for filling with TOA acrylic acrylic filler.
Around the crack. Wider than 1 mm. or a different continuity.
Putty for filling with TOA Acrylic Sealant.

TOA SUPERSHIELD ALKALI RESISTING PRIMER

Technical Data Sheet

Rev.1 10/2017

Coating system

Primer	Apply 1 coat of SUPERSHIELD ALKALI RESISTING PRIMER
Topcoat	Apply 2-3 coats of SUPERSHIELD , SUPERSHIELD DURACLEAN and SUPERSHIELD DURACLEAN A PLUS
	** remark for special system

HANDLING AND STORAGE

Storage condition

: The product must be stored in accordance with national regulations.
Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.
Containers must be kept tightly closed.

Shelf life

: 5 years at 30-35 ^{O}C.

HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

ทีโอเอ สีรองพื้นปูนใหม่กันด่าง ซุปเปอร์ซิลด์

ข้อมูลทางวิชาการ

ทบทวนครั้งที่ 1 10/2560

คุณสมบัติ

เป็นสีรองพื้นปูนใหม่กันด่าง ที่ทำจากอะคริลิคชนิดพิเศษ สามารถทนต่อความเป็นด่างจากพื้นผิวปูนฉาบ กระเบื้องแผ่นเรียบ หรือคอนกรีต เป็นเลิศ จึงป้องกันสีทับหน้า ไม่ให้สีเป็นรอยได้เป็นอย่างดี ปราศจากสารปรอทและตะกั่ว และสามารถต้านทาน เชื้อราในฟิล์มสีได้ดี ช่วยให้สีทับหน้าไม่เกิดรอยด่าง หรือเสื่อมสภาพก่อนเวลาอันสมควร

การใช้งาน เหมาะสำหรับเป็นสีรองพื้นปูนใหม่ โดยเฉพาะปูนฉาบ กระเบื้องแผ่นเรียบทั้งภายในและภายนอกอาคาร

ข้อมูลทางเทคนิค

ประเภทสี	สีน้ำทาอาคารจากเนื้ออะคริลิกแท้100%	
เฉดสี	ขาว	
ลักษณะฟิล์มสี	ชนิดด้าน	
เนื้อสีโดยปริมาตร	34-36	%
เนื้อสีโดยน้ำหนัก	52-54	%
จุดวาบไฟ	N/A	˚C
ปริมาณสารอินทรีย์ระเหยได้	น้อยกว่า 10	กรัม ต่อ ลิตร
ความหนาฟิล์มสีเมื่อเปียก	100-110	ไมครอน
ความหนาฟิล์มสีเมื่อแห้ง	35-40	ไมครอน
การครอบคลุมพื้นที่ตามทฤษฎี	35-45	ตารางเมตร ต่อ แกลลอน ต่อ เที่ยว

หมายเหตุ : การผสม, การใช้งาน, ความหยาบและรูพรุนของพื้นผิว มีผลต่อค่าการปกคลุมพื้นผิว

ระยะเวลาแห้งสัมผัส (อุณหภูมิ25-30˚C)	30	นาที
ระยะเวลาแห้งทาทับ (อุณหภูมิ25-30˚C)	2	ชั่วโมง
ระยะเวลาแห้งสมบูรณ์ (อุณหภูมิ25-30˚C)	7	วัน

มาตรฐานอ้างอิง

มาตรฐานอุตสาหกรรม 1123-2555(สีรองพื้นสำหรับงานปูน)
ฉลากเขียวไทย

วิธีใช้งาน

อุปกรณ์	ลูกกลิ้ง แปรงทาสี เครื่องพ่น	
ตัวเจือจาง	น้ำสะอาด	
การเจือจาง (%)	10-20	% (กลิ้ง หรือ ทา)
	20-25	% (พ่น)

อัตราส่วนดังกล่าวเป็นอัตราส่วนการเฉลี่ยจากการใช้งานจริง
การผสมน้ำให้ทำเมื่อต้องการปรับสภาพความข้นเหลวให้เหมาะสมกับ
สภาพการใช้งานตามสภาพอุณหภูมิอากาศและความชื้นสัมพัทธ์

ระบบการใช้งาน

การเตรียมพื้นผิว

พื้นผิวใหม่

ทำความสะอาดผนังให้ปราศจากเศษฝุ่นผง เศษซีเมนต์ และคราบไข
บริเวณที่มีรอยแตกร้าวความกว้างน้อยกว่า 1 มิลลิเมตรและไม่แตกต่อเนื่อง
ให้อุดโป๊วด้วยทีโอเอ อะครีลิค ฟิลเลอร์
บริเวณที่มีรอยแตกร้าว ความกว้างมากกว่า 1 มิลลิเมตรหรือมีการแตกต่อเนื่อง
ให้อุดโป๊วด้วย ทีโอเอ อะครีลิค ซิลแลนท์

ข้อมูลทางวิชาการ

ทบทวนครั้งที่ 1 10/2560

ระบบการทาสี

สีรองพื้น	ทาสีรองพื้นปูนใหม่กันด่าง ซุปเปอร์ซิลด์ 1 เที่ยว
สีทับหน้า	ทาสีทับหน้า ซุปเปอร์ซิลด์ ชนิดเนียน กึ่งเงาหรือเงา , ซุปเปอร์ซิลด์ ดูราคลีน และซุปเปอร์ซิลด์ ดูราคลีน เอ พลัส จำนวน 2-3 เที่ยว

การเก็บรักษา

สภาวะการเก็บรักษา	: จัดเก็บสินค้าในที่แห้ง มีอากาศถ่ายเทดี ปิดฝาให้สนิท ให้แน่นตลอดเวลา ไม่ควรเก็บในที่ร้อนและไม่ให้ถูกแสงแดดโดยตรง
อายุผลิตภัณฑ์	: 5 ปี ที่อุณหภูมิ 30-35 องศาเซลเซียส

ข้อมูลสุขภาพและความปลอดภัย

: กรุณาดูข้อควรระวังที่ติดไว้บนภาชนะบรรจุ การทำงานสีควรทำในที่ที่อากาศถ่ายเทสะดวก ควรใส่หน้ากากเมื่อทำการพ่นสีและพยายามเลี่ยงมิให้สัมผัสผิวหนัง หรือสูดดม ถ้าสีหกใส่ผิวหนังควรล้างด้วยน้ำสะอาดกับสบู่ทันที ถ้าสีเข้าตาควรล้างด้วยน้ำสะอาดทันทีและรีบไปพบแพทย์

: รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในข้อมูลด้านความปลอดภัย

การสงวนสิทธิ์เรียกร้อง

: รายละเอียดข้างบนนี้ได้มาโดยการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไปใช้ในสภาวะแตกต่างกันเราจึงไม่สามารถรับประกันในสิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น **บริษัทขอสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมิต้องแจ้งล่วงหน้า**