TOA
TOA POLYURETHANE 1K GLOSS FOR EXTERIOR #T-4000

Technical Data Sheet

Rev.1 10/2017

FEATURES

TOA Polyurethane 1K Gloss For Exterior #T-4000 is a one pack moisture cured polyurethane, suitable for interior wood floor that some time exposed to sunlight. This product is easy to use, provides high gloss, good scratch resistance, also abrasion resistance, impact resistance and chemical resistance.
Suitable for all interior woodworks such as parquet, indoor gymnasium and wooden furniture.

TECHNICAL INFORMATION

Type	Polyurethane	
Color	Clear	
Film appearance	Gloss	
Solid by volume	48	%
Solid by weight	44.0 ± 2.0	%
Flash point	29.4	˚C
Volatile organic compounds (VOCs)	NA	gram / liter
Wet film thickness	100	microns
Dry film thickness	45	microns
Theoretical coverage.	9-11	sq.m. / liter / coat
	35 – 45	sq.m. / gallon / coat
	Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.	
Touch dry (25-30˚C)	30 – 40	minutes.
Recoat dry (25-30˚C)	4	hours.
Full cure (25-30˚C)	7	days.

REFERENCE STANDARD

-

APPLICATION

Tools	Brush, Spray Gun	
Potlife	8 hours. (in closed can at 25 – 30 ˚C)	
Thinner No.	TOA Polyurethane Thinner No.41	
Dilution (%)	10	% (brush)
	30	% (spray)

APPLICATION SYSTEM

Surface Preparation

Old surface

The surface must be clean and free of dirt, grease, oil, wax, salt, old paint and other contaminants.

New surface

1. Use TOA abrasive paper no. 240 – 320 to sand the wood surface until smooth.
2. Fill all wood crack and hole by filler.
3. Sand again until the smooth surface is obtained.
4. Clean the surface until no dust remain.

TOA
TOA POLYURETHANE 1K
GLOSS FOR EXTERIOR #T-4000

Technical Data Sheet

Rev.1 10/2017

Coating system

Primer

1. Apply by brush with TOA Wood Preservative 1 coat. (Recoatable time is at least 30 minutes)
2. Apply by brush with TOA Wood Primer #T-2000 1 coat. (Recoatable time is at least 1 hour)

Topcoat

1. Mixing ratios between TOA Polyurethane #T-4000 and TOA Polyurethane Thinner No.41 are 10:3 for first coat and 10:1 for second and third coat, respectively.
2. Apply by brush with TOA Polyurethane 1K Gloss For Exterior #T-4000 at least 3 coats. (Recoatable time is at least 4 hours)
3. Before topcoat any layer, TOA abrasive paper no. 320 – 400 are recommended to sand the surface which provide good intercoat adhesion and smooth the surface.

Recommendation

: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure correct drying.

HANDLING AND STORAGE

Storage condition

: The product must be stored in accordance with national regulations.
Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.
Containers must be kept tightly closed.

Shelf life

: 2 years.

HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with s uitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

ทีโอเอ
ทีโอเอ โพลียูรีเทน 1 ส่วน ชนิดเงา สำหรับภายนอก #T-4000

ข้อมูลทางวิชาการ

ทบทวน ครั้งที่ 1 10/2560

คุณสมบัติ

ทีโอเอ โพลียูรีเทน 1 ส่วน ชนิดเงา สำหรับภายนอก #T-4000 เป็นโพลียูรีเทนชนิดที่แห้งแข็งโดยทำปฏิกิริยากับความชื้นในอากาศ เหมาะสำหรับพื้นไม้ภายในที่มีแดดส่องถึงเป็นบางเวลา ทาง่าย ให้ความเงางามสูง ทนทานต่อการขุดขีด ทนทานต่อการขัดถู และ ทนต่อการกระแทกได้ดี ทนต่อกรด-ด่าง สารเคมี ได้ดีเยี่ยม
เหมาะสำหรับงานไม้ภายในทุกชนิด เช่น พื้นไม้ปาร์เก้ พื้นไม้สนามกีฬาในร่ม และ เฟอร์นิเจอร์ไม้

ข้อมูลทางเทคนิค

ประเภทสี	โพลียูรีเทน	
เฉดสี	ใส	
ลักษณะฟิล์มสี	เงา	
เนื้อสีโดยปริมาตร	48	%
เนื้อสีโดยน้ำหนัก	44.0 ± 2.0	%
จุดวาบไฟ	29.4	˚C
ปริมาณสารอินทรีย์ระเหยได้	ไม่มีข้อมูล	กรัม/ลิตร
ความหนาฟิล์มสีเมื่อเปียก	100	ไมครอน
ความหนาฟิล์มสีเมื่อแห้ง	45	ไมครอน
การครอบคลุมพื้นที่ตามทฤษฎี	9-11	ตารางเมตร ต่อ ลิตร ต่อ เที่ยว
	35 – 45	ตารางเมตร ต่อ แกลลอน ต่อ เที่ยว
	หมายเหตุ : การผสม, การใช้งาน, ความหยาบและรูพรุนของพื้นผิว มีผลต่อค่าการปกคลุมพื้นผิว	
ระยะเวลาแห้งสัมผัส (อุณหภูมิ25-30˚C)	30 – 40	นาที
ระยะเวลาแห้งทาทับ (อุณหภูมิ25-30˚C)	4	ชั่วโมง
ระยะเวลาแห้งสมบูรณ์ (อุณหภูมิ25-30˚C)	7	วัน

มาตรฐานอ้างอิง

-

วิธีใช้งาน

อุปกรณ์	แปรงทาสี เครื่องพ่น
อายุการใช้งานหลังผสม	8 ชั่วโมง (ในภาชนะปิด ทดสอบที่ 25 – 30 ˚C)
ทินเนอร์	ทีโอเอ โพลียูรีเทน ทินเนอร์ เบอร์ 41
การผสมทินเนอร์ (%)	10 % (ทา)
	30 % (พ่น)

ระบบการใช้งาน

การเตรียมพื้นผิว

พื้นผิวเก่า

พื้นผิวที่จะใช้งานต้องสะอาด ปราศจากฝุ่น, คราบไข, คราบน้ำมัน, แวกซ์, คราบเกลือ, สีเก่า และสิ่งปนเปื้อนต่างๆ

พื้นผิวใหม่

1. ใช้กระดาษทรายขัดแห้ง ทีโอเอ ดีเอสซี #240 – 320 ขัดแต่งพื้นผิวจนเรียบสวย
2. อุดโป๊วรอยแตก ตำหนิบนไม้และหัวตะปู ให้เรียบร้อย
3. ขัดแต่งด้วยกระดาษทรายอีกครั้ง จนได้พื้นผิวที่เรียบเนียน
4. เช็ดทำความสะอาดพื้นผิว

ระบบการทาสี

สีรองพื้น

1. ทารองพื้นด้วย ทีโอเอ น้ำยารักษาเนื้อไม้ จำนวน 1 เที่ยว
   (ทิ้งให้แห้งอย่างน้อย 30 นาที ก่อนทาทับเที่ยวต่อไป)
2. ทารองพื้นด้วย ทีโอเอ วูดโพรเมอร์ #T-2000 จำนวน 1 เที่ยว
   (ทิ้งให้แห้งอย่างน้อย 1 ชั่วโมง ก่อนทาทับเที่ยวต่อไป)

ทีโอเอ
ทีโอเอ โพลียูรีเทน 1 ส่วน
ชนิดเงา สำหรับภายนอก #T-4000

ข้อมูลทางวิชาการ

ทบทวน ครั้งที่ 1 10/2560

สีทับหน้า	1. การผสม ทีโอเอ โพลียูรีเทน #T-4000 กับ ทีโอเอ โพลียูรีเทน ทินเนอร์ เบอร์ 41 การทาเที่ยวที่ 1 แนะนำให้ผสมสี 10 ส่วน ต่อ ทินเนอร์ 3 ส่วน การทาเที่ยวที่ 2 และ 3 แนะนำให้ผสมสี 10 ส่วน ต่อ ทินเนอร์ 1 ส่วน 2. ทาด้วย ทีโอเอ โพลียูรีเทน 1 ส่วน ชนิดเงา สำหรับภายนอก #T-4000 อย่างน้อย 3 เที่ยว (ทิ้งให้แห้งอย่างน้อย 4 ชั่วโมง ก่อนทาทับเที่ยวต่อไป) 3. ก่อนทาหรือพ่นทับหน้าเที่ยวต่อไป ให้ขัดแต่งพื้นผิวด้วยกระดาษทราย ทีโอเอ ดีเอสซี #320 – 400 เพื่อเพิ่มการยึดเกาะและได้พื้นผิวชิ้นงานที่เรียบ
ข้อแนะนำการปฏิบัติงาน	: อุณหภูมิของชิ้นงานจะต้องสูงกว่า 10˚C และสูงกว่าจุดน้ำค้างอย่างน้อย 3˚C อุณหภูมิและความชื้นสัมพัทธ์ต่างมีผลต่อชิ้นงานและการแห้งตัวของฟิล์มสี

การเก็บรักษา

สภาวะการเก็บรักษา	: จัดเก็บสินค้าในที่แห้ง มีอากาศถ่ายเทดี ปิดฝาให้สนิท ให้แน่นตลอดเวลา ไม่ควรเก็บในที่ร้อนและไม่ให้ถูกแสงแดดโดยตรง
อายุผลิตภัณฑ์	: 2 ปี

ข้อมูลสุขภาพและความปลอดภัย

: กรุณาดูข้อควรระวังที่ติดไว้บนภาชนะบรรจุ การทำงานสีควรทำในที่ที่อากาศถ่ายเทสะดวก
ควรใส่หน้ากากเมื่อทำการพ่นสีและพยายามเลี่ยงมิให้สัมผัสผิวหนัง หรือสูดดม
ถ้าสีหกใส่ผิวหนังควรล้างด้วยน้ำสะอาดกับสบู่ทันที ถ้าสีเข้าตาควรล้างด้วยน้ำสะอาดทันทีและรีบไปพบแพทย์
: รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในข้อมูลด้านความปลอดภัย

การสงวนสิทธิ์เรียกร้อง

: รายละเอียดข้างบนนี้ได้มาโดยการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไปใช้ในสภาวะแตกต่างกันเราจึงไม่สามารถรับประกันในสิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น
บริษัทขอสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมิต้องแจ้งล่วงหน้า